
 t _{work}	 t _{cure}
RM 700	50-90 °F (10-32 °C)	20-30 min	4-5 hrs / 10-12 hrs / 2-7 d
RM 710	30-80 °F (-1-27 °C)	10-15 min	3-4 hrs / 6-8hrs / 2-7 d

